

AlphaSeal® 4609-65 REV1 BLUE 7002 (HC)

PVC, Flexible

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	11.9	MPa	ASTM D 638
Elongation at Break	345	%	ASTM D 638
Shore A Hardness	65	-	ASTM D 2240
Other Standards^[S]			
Modulus at 100% Elongation	4.79	MPa	ASTM D 638

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1190	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Regional Availability

North America, Europe

Certifications

Food contact, Food approval FDA 21 CFR, Drinking water contact