

**Geon™ BIO HC5155**

PVC, Flexible

GEON Performance Solutions

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Break	<b>8.62</b>	MPa	ASTM D 638
Elongation at Break	<b>400</b>	%	ASTM D 638
Shore A Hardness	<b>55</b>	-	ASTM D 2240

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Biobased content	<b>25</b>	%	-
Density	<b>1160</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Melt temperature	<b>177 - 182</b>	°C	-

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Delivery form**

Pellets

**Additives**

Plasticizer

**Certifications**

Contains renewable resources

**Applications**

Electrical and Electronical, Medical

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa