

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	10	MPa	ASTM D 638
Elongation at Break	390	%	ASTM D 638
Shore A Hardness	65	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Biobased content	25	%	-
Density	1190	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	182 - 188	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Additives

Plasticizer

Certifications

Contains renewable resources

Applications

Electrical and Electronical, Medical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa