

Geon™ HC 2155

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	10.3	MPa	ASTM D 638
Elongation at Break	540	%	ASTM D 638
Shore A Hardness	55	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1160	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Pipe/Tube Extrusion, Other Extrusion

Delivery form

Pellets

Additives

Plasticizer

Special Characteristics

Transparent

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Electrical and Electronical, Medical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa