

Geon™ Vinyl Flexible 82024

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	7.58	MPa	ASTM D 638
Elongation at Break	450	%	ASTM D 638
Shore A Hardness	52	-	ASTM D 2240
Tear Strength	19.3	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Applications

Automotive, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa