

Geon™ Vinyl Flexible 90054

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	12.8	MPa	ASTM D 638
Elongation at Break	250	%	ASTM D 638
Shore A Hardness	84	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1300	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Features

Fungus Resistance

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa