

## Geon™ Vinyl Flexible 90213

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break	8.96	MPa	ASTM D 638
Elongation at Break	270	%	ASTM D 638
Shore A Hardness	66	-	ASTM D 2240
Tear Strength	42	kN/m	ASTM D 624
<b>Other properties</b>			
Density	1330	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding

#### Delivery form

Pellets

#### Applications

Automotive, Encapsulation

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa