

Geon™ Vinyl Flexible 90401

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	14.2	MPa	ASTM D 638
Elongation at Break	310	%	ASTM D 638
Shore A Hardness	75	-	ASTM D 2240
Tear Strength	36	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	1240	kg/m ³	ASTM D 792

Characteristics**Processing**

Blow Molding

Delivery form

Pellets

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa