

Geon™ Vinyl Flexible B6DE3

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	21.8	MPa	ASTM D 638
Elongation at Break	320	%	ASTM D 638
Shore D Hardness	42	-	ASTM D 2240
Tear Strength	125	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	1280	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Features

Blush Resistance/Low Crease Whitening

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa