

## Geon™ Vinyl Flexible B7501

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break	13.1	MPa	ASTM D 638
Elongation at Break	380	%	ASTM D 638
Shore A Hardness	75	-	ASTM D 2240
Tear Strength	43.8	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	1270	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding, Other Extrusion

#### Delivery form

Pellets

#### Certifications

Drinking water contact, Drinking water contact NSF 61

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa