

Geon™ Vinyl Flexible B9500

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	19.2	MPa	ASTM D 638
Elongation at Break	360	%	ASTM D 638
Shore A Hardness	87	-	ASTM D 2240
Shore D Hardness	52	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1270	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	193 - 204	°C	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa