

**Geon™ Vinyl Flexible C80B1 WHITE 1473**

PVC, Flexible

GEON Performance Solutions

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Break	<b>11.3</b>	MPa	ASTM D 638
Elongation at Break	<b>310</b>	%	ASTM D 638
Shore A Hardness	<b>79</b>	-	ASTM D 2240
Compression Set , 22 hr @ 73 °F	<b>25</b>	%	ASTM D 395

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1380</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Melt temperature	<b>193 - 204</b>	°C	-

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Delivery form**

Pellets, White

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa