

Geon™ Vinyl Flexible C8002

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	12.1	MPa	ASTM D 638
Elongation at Break	280	%	ASTM D 638
Shore A Hardness	80	-	ASTM D 2240
Tear Strength	43.8	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	1400	kg/m ³	ASTM D 792

Characteristics

Processing

Pipe/Tube Extrusion, Profile Extrusion

Delivery form

Pellets

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa