

Geon™ Vinyl Flexible G8024

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	17.1	MPa	ASTM D 638
Elongation at Break	320	%	ASTM D 638
Shore A Hardness	77	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1240	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	188 - 199	°C	-

Characteristics

Processing

Injection Molding, Pipe/Tube Extrusion, Other Extrusion

Delivery form

Pellets

Special Characteristics

Transparent

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa