

Geon™ Vinyl Flexible MG26

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	14.3	MPa	ASTM D 638
Elongation at Break	250	%	ASTM D 638
Shore A Hardness	80	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1450	kg/m ³	ASTM D 792

Characteristics

Processing

Pipe/Tube Extrusion, Profile Extrusion, Other Extrusion

Delivery form

Pellets

Applications

Automotive, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa