

Geon™ Vinyl Flexible R115AE Natural

PVC, Flexible

GEON Performance Solutions

| Mechanical properties | Value | Unit | Test Standard |
|---------------------------|-------|------|---------------|
| ASTM Data | | | |
| Tensile Strength at Break | 16.2 | MPa | ASTM D 638 |
| Elongation at Break | 280 | % | ASTM D 638 |
| Shore A Hardness | 85 | - | ASTM D 2240 |

| Other properties | Value | Unit | Test Standard |
|------------------|-------|-------------------|---------------|
| Density | 1370 | kg/m ³ | ASTM D 792 |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|---|-----------|------|---------------|
| Melt temperature | 188 - 199 | °C | - |

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Applications

Building Construction

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa