

Geon™ Vinyl Flexible R157AE

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	18.8	MPa	ASTM D 638
Elongation at Break	300	%	ASTM D 638
Shore A Hardness	91	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1320	kg/m ³	ASTM D 792

Characteristics

Processing

Other Extrusion

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather

Applications

Automotive, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa