

## Geon™ Vinyl Flexible R235AE White 1875

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break	18.6	MPa	ASTM D 638
Elongation at Break	280	%	ASTM D 638
Shore A Hardness	82	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1400	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	193 - 204	°C	-

### Characteristics

#### Processing

Injection Molding, Profile Extrusion, Other Extrusion

#### Delivery form

Pellets, White

#### Features

Melt Strength

#### Applications

Automotive

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa