

Geon™ Vinyl Flexible R323AE

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	16.5	MPa	ASTM D 638
Elongation at Break	400	%	ASTM D 638
Shore A Hardness	69	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1280	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	188 - 199	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Features

Good Adhesion

Applications

Building Construction

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa