

## Geon™ Vinyl Flexible R352AE

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break	15.9	MPa	ASTM D 638
Elongation at Break	300	%	ASTM D 638
Shore A Hardness	79	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1370	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	193 - 204	°C	-

### Characteristics

#### Processing

Injection Molding, Profile Extrusion, Other Extrusion

#### Delivery form

Pellets

#### Special Characteristics

U.V. stabilized or stable to weather

#### Applications

Automotive, General Purpose

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa