

## Geon™ Vinyl Flexible R881C

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break	10	MPa	ASTM D 638
Elongation at Break	400	%	ASTM D 638
Shore A Hardness	57	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1160	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	182 - 193	°C	-

### Characteristics

#### Processing

Injection Molding, Other Extrusion

#### Delivery form

Pellets

#### Special Characteristics

Transparent

#### Applications

Building Construction

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa