

Geon™ Vinyl Flexible R999A Black

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	13.8	MPa	ASTM D 638
Elongation at Break	280	%	ASTM D 638
Shore A Hardness	82	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1450	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	193 - 204	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets, Black

Applications

Automotive, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa