

## Geon™ Vinyl Flexible R1700D

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break	18.6	MPa	ASTM D 638
Elongation at Break	280	%	ASTM D 638
Shore D Hardness	58	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Limiting Oxygen Index	26	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1500	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Other Extrusion

#### Delivery form

Pellets

#### Applications

Automotive

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa