

Geon™ Vinyl Flexible XV3581G

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	21.2	MPa	ASTM D 638
Elongation at Break	280	%	ASTM D 638
Shore A Hardness	88	-	ASTM D 2240
Tear Strength	101	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	1280	kg/m ³	ASTM D 792

Characteristics

Processing

Other Extrusion

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa