

Geon™ Vinyl Flexible XV3844

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	18.4	MPa	ASTM D 638
Elongation at Break	420	%	ASTM D 638
Shore A Hardness	74	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1210	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Certifications

Food contact, Food approval FDA 21 CFR

Special Characteristics

Transparent

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa