

Geon™ Vinyl Flexible XV3875

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	17.2	MPa	ASTM D 638
Elongation at Break	350	%	ASTM D 638
Shore A Hardness	78	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding, Pipe/Tube Extrusion, Other Extrusion

Delivery form

Pellets

Special Characteristics

Transparent

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa