

Geon™ Vinyl Flexible Y126 White 317

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	15.2	MPa	ASTM D 638
Elongation at Break	400	%	ASTM D 638
Shore A Hardness	67	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	22	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	193 - 204	°C	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Delivery form

Pellets, White

Features

Good Adhesion

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa