

## Geon™ Vinyl Wire & Cable W780L

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break	24.8	MPa	ASTM D 638
Elongation at Break	350	%	ASTM D 638
Shore D Hardness	43	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Limiting Oxygen Index	30	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1280	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Wire/Cable Extrusion

#### Delivery form

Pellets

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa