

Geon™ Vinyl Wire & Cable W2403L

PVC, Flexible

GEON Performance Solutions

| Mechanical properties | Value | Unit | Test Standard |
|---------------------------|-------|------|---------------|
| ASTM Data | | | |
| Tensile Strength at Break | 22.3 | MPa | ASTM D 638 |
| Elongation at Break | 250 | % | ASTM D 638 |
| Shore D Hardness | 43 | - | ASTM D 2240 |

| Thermal properties | Value | Unit | Test Standard |
|-----------------------|-------|------|---------------|
| ASTM Data | | | |
| Limiting Oxygen Index | 28 | % | ASTM D 2863 |

| Other properties | Value | Unit | Test Standard |
|------------------|-------|-------------------|---------------|
| Density | 1430 | kg/m ³ | ASTM D 792 |

Characteristics

Processing

Wire/Cable Extrusion, Coating

Delivery form

Pellets

Special Characteristics

Flame retardant

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa