

MM-PVC E 1561

PVC, Flexible

MACOMASS Verkaufs AG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	10	MPa	ISO 527
Strain at break	300	%	ISO 527
Shore A hardness	64	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	1170	kg/m ³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Melt temperature	155 - 165	°C	-
Zone 1	125 - 160	°C	-

Characteristics**Processing**

Other Extrusion

Special Characteristics

Transparent

Additives

Plasticizer

Regional Availability

Europe