

MM-PVC E 1570

PVC, Flexible

MACOMASS Verkaufs AG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	11	MPa	ISO 527
Strain at break	300	%	ISO 527
Shore A hardness	70	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	1170	kg/m ³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Feed temperature	135	°C	-
Nozzle temperature	170	°C	-

Characteristics**Processing**

Other Extrusion

Regional Availability

Europe

Additives

Plasticizer