

MM-PVC E 1585

PVC, Flexible

MACOMASS Verkaufs AG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	17	MPa	ISO 527
Strain at break	250	%	ISO 527
Shore A hardness	88	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	1240	kg/m ³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Feed temperature	135	°C	-
Nozzle temperature	170	°C	-

Characteristics**Processing**

Other Extrusion

Special Characteristics

Transparent

Additives

Plasticizer

Regional Availability

Europe