

MM-PVC E 1595

PVC, Flexible

MACOMASS Verkaufs AG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	20	MPa	ISO 527
Strain at break	200	%	ISO 527
Shore A hardness	95	-	ISO 7619-1
Shore D hardness	47	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	1260	kg/m ³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Feed temperature	135	°C	-
Nozzle temperature	170	°C	-

Characteristics**Processing**

Other Extrusion

Special Characteristics

Transparent

Additives

Plasticizer

Regional Availability

Europe