

MM-PVC I 1595

PVC, Flexible

MACOMASS Verkaufs AG

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Tensile Strength | 18 | MPa | ISO 527 |
| Strain at break | 250 | % | ISO 527 |
| Shore A hardness | 95 | - | ISO 7619-1 |
| Shore D hardness | 46 | - | ISO 7619-1 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1250 | kg/m ³ | ISO 1183 |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| Melt temperature | 170 | °C | - |
| Mold temperature | 30 | °C | - |

Characteristics**Processing**

Injection Molding

Special Characteristics

Transparent

Additives

Plasticizer

Regional Availability

Europe