

**POLYVIN PVC 5819N**

PVC, Flexible

LyondellBasell Industries

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Break	<b>8</b>	MPa	ASTM D 638
Elongation at Break	<b>250</b>	%	ASTM D 638
Shore A Hardness	<b>50</b>	-	ASTM D 2240

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1280</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America

**Applications**

Automotive