

POLYVIN PVC 5819ND

PVC, Flexible

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	12.4	MPa	ASTM D 638
Elongation at Break	250	%	ASTM D 638
Shore A Hardness	80	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1250	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America

Applications

Automotive