

POLYVIN PVC 9020N

PVC, Flexible

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	12.8	MPa	ASTM D 638
Elongation at Break	200	%	ASTM D 638
Shore D Hardness	37	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1320	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America

Applications

Automotive