

**3014**

PVC

Westlake Chemical Corp.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>2620</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>48.3</b>	MPa	ASTM D 638
Flexural Modulus	<b>3103</b>	MPa	ASTM D 790
Flexural Strength	<b>82.7</b>	MPa	ASTM D 790
Shore D Hardness	<b>78</b>	-	ASTM D 2240
Izod Impact notched, 1/8 in	<b>64.1</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Coefficient of Thermal Expansion, MD	<b>122</b>	E-6/K	ASTM D 696
DTUL @ 264 psi	<b>65.6</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1380</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Special Characteristics**

Flame retardant

**Regional Availability**

North America

**Chemical Resistance**

General Chemical Resistance