

**Product Texts**

Durometer A, 15 Second, (1/4"/24 Hr)

Test Method: ASTM D 2240

Result: 55 +/- 3

Tensile Strength, (75 mil)

Test Method: ASTM D 638

Result: 1500 psi

Elongation, (75 mil)

Test Method: ASTM D 638

Result: 425 %

Modulus 100%, (75 mil)

Test Method: ASTM D 638

Result: 460 psi

Graves Tear Strength

Test Method: ASTM D 1004

Result: 210 ppi

Brittle Point

Test Method: ASTM D 746

Result: -47.5 °C

Recommended Processing Temp.: 320 - 350 °F

Other properties	Value	Unit	Test Standard
Density	1200	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Delivery form**

Black

**Applications**

Automotive, General Purpose

**Features**

Fungus Resistance

**Regional Availability**

North America, Europe