

| Mechanical properties | Value | Unit | Test Standard |
|--------------------------------------|-------|------|---------------|
| ASTM Data | | | |
| Tensile Strength | 16 | MPa | ASTM D 638 |
| Elongation at Break | 385 | % | ASTM D 638 |
| Shore A Hardness | 68 | - | ASTM D 2240 |
| Other Standards^[S] | | | |
| Modulus at 100% Elongation | 5.14 | MPa | ASTM D 638 |

S: These properties are reported by the producer according standards that are different to our defaults.

| Other properties | Value | Unit | Test Standard |
|------------------|-------|-------------------|---------------|
| Density | 1200 | kg/m ³ | ASTM D 792 |

Characteristics

Processing

Other Extrusion

Special Characteristics

Transparent

Features

Blush Resistance/Low Crease Whitening

Certifications

Food contact, Food approval FDA 21 CFR, Medical Grade

Applications

Medical

Regional Availability

North America, Europe