

Beobase 50/50 PVC standard extrusion

PVC-W50

Beologic nv

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	6100	MPa	ISO 527
Tensile Strength	35.5	MPa	ISO 527
Strain at break	0.85	%	ISO 527
Flexural modulus, 23°C	5300	MPa	ISO 178
Flexural strength	64.3	MPa	ISO 178

Other properties	Value	Unit	Test Standard
Density	1400	kg/m ³	ISO 1183
Biobased content	50	%	-
Bulk density	600	kg/m ³	-

Characteristics**Processing**

Other Extrusion

Certifications

Contains renewable resources

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

Europe, Near East/Africa