

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2340	MPa	ISO 527
Tensile Strength	21.8	MPa	ISO 527
Flexural modulus, 23°C	3850	MPa	ISO 178

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Coefficient of Thermal Expansion, MD	36	E-6/K	ASTM D 696

Electrical properties	Value	Unit	Test Standard
ISO Data			
Surface resistivity	8.1E14	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Biobased content	60	%	-
Density	1460	kg/m ³	ASTM D 792

Characteristics

Processing

Profile Extrusion

Certifications

Contains renewable resources

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

Europe