

CELSTRAN® PEHD-GF40-01

(PE-HD)-GLF60

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	8250	MPa	ISO 527
^[C] Stress at break	120	MPa	ISO 527
^[C] Strain at break	2.3	%	ISO 527
^[C] Charpy notched impact strength, +23°C	40	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1270	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Features

Long fiber reinforced

Regional Availability

North America, Europe, Asia Pacific