

7066

PVC

Tekni-Plex

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	15.9	MPa	ASTM D 638
Modulus at 100% Elongation	6.89	MPa	ASTM D 412
Shore A Hardness	70	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1260	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding, Other Extrusion

Applications

Medical

Additives

Plasticizer

Regional Availability

North America, Europe, Asia Pacific

Features

Low Odor