

8607

PVC

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2537	MPa	ASTM D 638
Tensile Strength at Yield	39.2	MPa	ASTM D 638
Flexural Modulus	1924	MPa	ASTM D 790
Flexural Strength	63.4	MPa	ASTM D 790
Shore D Hardness	78.5	-	ASTM D 2240
Izod Impact unnotched, 1/8 in	1160	J/m	ASTM D 256
Izod Impact unnotched, 1/4 in	288	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	72.2	°C	ASTM D 648
DTUL @ 264 psi	66.1	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1380	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Special Characteristics

High impact or impact modified

Delivery form

Pellets

Regional Availability

North America