

9275 J Clear 38

PVC

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2827	MPa	ASTM D 638
Flexural Strength	89.6	MPa	ASTM D 790
Izod Impact notched, 1/8 in	26.7	J/m	ASTM D 256
Izod Impact notched, 1/4 in	16	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	56	°C	ASTM D 648

Optical properties	Value	Unit	Test Standard
ASTM Data			
Haze	5	%	ASTM D 1003
Light Transmittance	80	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	1330	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Blow Molding

Applications

Medical, Packaging

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America