

Formolon® AW04

PVC

Formosa Plastics Corporation

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2827	MPa	ASTM D 638
Tensile Strength	49.6	MPa	ASTM D 638
Izod Impact notched, 1/8 in	58.7	J/m	ASTM D 256

Characteristics**Processing**

Pipe/Tube Extrusion, Other Extrusion

Certifications

Drinking water contact, Drinking water contact NSF 61

Features

Homopolymer

Regional Availability

North America