

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2720	MPa	ASTM D 638
Tensile Strength at Yield	48.9	MPa	ASTM D 638
Flexural Modulus	2970	MPa	ASTM D 790
Flexural Strength	93.1	MPa	ASTM D 790
Shore D Hardness	78	-	ASTM D 2240
Izod Impact notched, 1/8 in	51	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Coefficient of Thermal Expansion, MD	66	E-6/K	ASTM D 696

Other properties	Value	Unit	Test Standard
Density	1280	kg/m ³	ASTM D 792

Characteristics

Processing

Other Extrusion

Applications

Building Construction

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa