

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	2990	MPa	ASTM D 638
Tensile Strength at Yield	45	MPa	ASTM D 638
Flexural Modulus	2940	MPa	ASTM D 790
Flexural Strength	80.7	MPa	ASTM D 790
Shore D Hardness	79	-	ASTM D 2240
Izod Impact notched, 1/8 in	80	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Coefficient of Thermal Expansion, MD	64	E-6/K	ASTM D 696
DTUL @ 66 psi	93.9	°C	ASTM D 648
DTUL @ 264 psi	86.1	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1250	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Profile Extrusion, Other Extrusion

### Delivery form

Pellets

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa