

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	2530	MPa	ASTM D 638
Tensile Strength at Yield	47.6	MPa	ASTM D 638
Elongation at Break	13	%	ASTM D 638
Flexural Modulus	2920	MPa	ASTM D 790
Flexural Strength	80.7	MPa	ASTM D 790
Shore D Hardness	81	-	ASTM D 2240
Izod Impact notched, 1/8 in	640	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	61.1	°C	ASTM D 648
DTUL @ 264 psi	55.6	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1410	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets

### Special Characteristics

High impact or impact modified

### Applications

General Purpose

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa